

Technical Data Sheet

# Interflon Fin Super (aerosol)

Universal dry-film lubricant

Dry lubricant with MicPol® Technology, with very good cleaning, lubricating and protective action. Penetrates, dissolves dirt, expels moisture and lubricates better and longer than conventional oils. Leaves a clean, dry lubricating film that does not drip, stain, adhere to dust or dirt and provides a long-term protection against moisture and corrosion.

## Application

Suitable for cleaning, removing rust and corrosion. For the lubrication of chains, cables, housings, cylinders, spindles, hinges, shafts, rods, locks, tools, valves, sunroofs, measuring equipment, door seals, weapons etc. Excellent replacement for lubricants with MoS2 or graphite and silicon spray.

## Advantages

- ⊖ Reduction of wear
- ⊖ Water resistant
- ⊖ Economic in use
- ⊖ Prevents moving parts/locks from freezing
- ⊖ Colourless/leaves no stains
- ⊖ Dissolves rust and frees sticking parts
- ⊖ Cleans and protects against corrosion
- ⊖ Contains no chlorinated solvents or silicones
- ⊖ Aerosol can be used in every position

## Instructions for use

Shake before use. Parts should be cleaned first with a solvent or alkaline cleaning agent. Spray Interflon Fin super (aerosol) onto parts such as cables and chains and allow to penetrate. Wipe off the excess of lubricant with a clean cloth.

*Note: Do not use too much Interflon Fin Super (aerosol). Applying a thin layer, with occasional re-lubrication, gives a better result than a thick layer.*

Property	Result	Method
Composition	Mixture of mineral and vegetable oils, additives and MicPol®.	
Colour	Yellow-brown	
Odour	Like oil	
Density @ 20°C	0.73 g/cm <sup>3</sup>	
Kinematic viscosity @ 40°C	21 cSt	ASTM D445
Pour point	< -43°C	ASTM D97
Lowest application temperature	-43°C	
Highest application temperature*	170°C	
Dielectric strength	128 kV/cm	IEC 60156
Conductivity	> 2000 pS/m	ASTM D2624
Shelf life**	6 years	

\* High temperature limit is valid after evaporation of solvent.

\*\* Shelf life of the product when stored at room temperature in the original and unopened packaging.

*This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale. Interflon®/MicPol® is a registered trademark of Interflon BV. Typical properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture. The information contained herein is subject to change without notice.*